

# CEMENT MODIFIER

# BOND R

## TECHNICAL DATA

### 1.0 DESCRIPTION

Bond-R is an acrylic polymer which when added to Portland cement compositions, greatly improves their physical and chemical performance, whether used indoor or outdoor.

The improvements obtained using Bond-R are superior to those achieved using P.V.A. and styrene-butadiene emulsions. The properties improved include tensile and flexural strengths, abrasion and impact resistance, adhesion to existing concrete and resistance to oil and grease.

### 2.0 PROPERTIES

2.1. Colour	White.
2.2. Specific Gravity	1.07.
2.3. Flash Point	Non-Flammable.
2.4. Viscosity	Low.
2.5. Toxicity	Non-Toxic.
2.6. D.G. Classification	Non-Hazardous.
2.7. Shelf Life	1 year in sealed containers as supplied (once opened product should be used within 3 months). Protect from frost.

### 3.0 USES

Uses for Bond R modified concrete and plaster include;

- Heavy duty flooring.
- Topping and patching mix for existing damaged floors.
- Levelling screed or underlay for decorative flooring.
- Terrazzo.
- Precast panels.
- Patching of spalled concrete.
- Bridge deck repairs.

### 4.0 APPLICATION INSTRUCTIONS

- 4.1. Air and surface temperature must be 5°C or higher during and for 4 days following application. Avoid use during very hot, dry weather as this may result in fine surface cracking.
- 4.2. BOND R should not be used on floors subject to rising damp.
- 4.3. Dust, loose or weak areas must be removed. Areas badly soaked with oil or grease must be chipped out. Oil, grease or paint on the surface can be removed by scouring with a hot detergent solution. The surface must then be rinsed thoroughly with clean water and left to dry.
- 4.4. When spalled concrete is being repaired all unsound material must be removed and all rusted reinforcing exposed. Remove rust and coat exposed steel with a suitable zinc rich primer.

# BOND R

---

## TECHNICAL DATA Continued

---

### 4.0 APPLICATION INSTRUCTIONS (continued)

#### 4.5. PRIMING

All surfaces to be coated or patched should be primed to ensure maximum bond

##### 4.5.1. Method A:

To a 1:1 mixture of BOND R and water add enough fresh cement to obtain a wet brushable slurry. Brush the slurry firmly into the surface to be coated and apply topping or patch material before the slurry coat has dried.

##### 4.5.2. Method B:

Brush a mixture of 1:1 BOND R and water over the surface to be coated at approximately 6m<sup>2</sup>/litre. Allow this coat to dry for 12 hours minimum. Apply a second coat to the surface and apply topping or patch material before this coating dries.

#### 4.6. MIXING

Dilute 1 part BOND R with between 1 and 4 parts water depending on intended use as below. Mix this liquid with the desired sand cement blend to obtain a semi-dry, plastic consistency. Mixing should not exceed one and a half minutes.

#### 4.7. MIX RATIOS

Suggested mix ratios for various applications are as follows:

##### 4.7.1. *Heavy Duty Flooring.*

3 parts suitably graded aggregate to 1 part cement.  
1 part BOND R to 1 part water as gauging liquid.

##### 4.7.2. *Patching and Spall Repair.*

2 parts hard plastering sand to 1 part cement.  
1 part BOND R to 1 part water as gauging liquid.

##### 4.7.3. *Light Duty Levelling Screed or Underlay.*

3 parts flooring sand to 1 part cement.  
1 part BOND R to 4 parts water as gauging liquid.

##### 4.7.4. *Tile Adhesive.*

3 parts of sand to 1 part cement.  
1 part BOND R to 2 parts water as gauging liquid.



**Strat  
more.**

Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

# BOND R

---

## TECHNICAL DATA Continued

---

### 4.8. LAYING

Spread the mix to the desired thickness, compact with a tamping bar and level with wooden floats. Close the surface with a metal float and do not rework after this. Do not cure with water. Avoid using during rapid drying conditions. Foot traffic may be allowed after 24 hours.

Full cure is obtained after 14 days.

4.8.1. Minimum application thickness will depend on the size of aggregate in the mix and service conditions. As a guide, heavy duty flooring should be a minimum of 6mm thick and light duty toppings of 1.5mm minimum.

### 5.0 PACKAGING

4, 20 and 200 litre containers.



Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.