

EPOXY MORTAR PUTTY EPAR EX

TECHNICAL DATA

1.0 DESCRIPTION

A two part, non-slump epoxy mortar specially formulated to allow hand mixing. Adheres strongly to dry or damp concrete, steel, glass, aluminium, etc. EPAR EX is non-shrink and has excellent chemical resistance.

Also available with a cold cure hardener for use from 0°C – 10° C and a 5-minute hardener which has a 5-minute pot life and 10-minute initial set time.

2.0 PHYSICAL PROPERTIES:

2.1	Viscosity	Non-Slump.
2.2	Mix Ratio	1 : 1 by weight or volume.
2.3	Pot Life	1 – 1.5 hours at 20°C. Std hardener.
2.4	Minimum Application Temp.	10°C. Std hardener.
2.5	Shelf Life	1 year in original unopened containers.
2.6	Cured Properties	(Standard hardener at 20°C)
2.6.1	Colour	Grey.
2.6.2	Specific Gravity	1.8
2.6.3	Compressive Strength	46 MPa 1 day, 71 MPa 7 days.
2.6.4	Compressive Modulus	13 GPa.
2.6.5	Tensile Strength	23 MPa.
2.6.6	Thermal Expansion	5x 10 ⁻⁵ mm/mm/°C.

3.0 USES

Uses include:

- 3.1 Assembly and repair of precast concrete units.
- 3.2 Repair of spalling concrete and protection of steel reinforcements.
- 3.3 Levelling of concrete floors exposed to heavy load or impact.
- 3.4 Grouting of horizontal or overhead starter bars or bolts.
- 3.5 Fabrication of concrete pipe intersections, etc.

4.0 APPLICATION INSTRUCTIONS

- 4.1 SURFACE PREPARATION. Thoroughly clean the jointing surfaces of all extraneous matter, especially oil and grease. Laitance should be removed from concrete surfaces mechanically or by acid etching. For best results steel surfaces should be prepared by sand blasting or grinding.

EPAR EX

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.2 MIXING. Accurately proportion required volume of resin and hardener ensuring this amount can be used within its pot life. Mix the two parts thoroughly by machine, spatula or hand until a uniform grey colour is obtained. Wear protective gloves during mixing and application. Wet gloves in water to prevent sticking of EPAR EX. Shake off excess water. Avoid mixing water with EPAR EX as this may interfere with the final set. In cold weather, the resin and hardener may be softened by placing the containers in hot water.
- 4.3 APPLICATION. EPAR EX should be worked well into the surface to be filled or bonded. Initially a thin smear should be applied to ensure the surface is properly "wet" with epoxy. After applying this initial layer more EPAR EX may be applied to the desired thickness. Both surfaces should be coated with EPAR EX before being joined.
- 4.3.1 Alternatively, surfaces should be primed with EPAR 122 before EPAR EX is applied. Brush EPAR 122 well into the surface and apply EPAR EX while EPAR 122 remains tacky.
- 4.3.2 A smooth surface may be obtained on EPAR EX by wiping with a wet cloth, trowel or fingers before initial cure.
- 4.4 CLEAN UP. Hands and equipment should be washed in soap and water before curing is advanced.
- 4.5 Refer to product data sheet for additional details.

5.0 PRECAUTIONS

Gloves must be worn when handling epoxy products.

Keep out of reach of children. Avoid contact with eyes and skin. Refer to safety data sheet for handling and first aid information.

Additional Information:

For optimal performance with any epoxy system it is important to:

1. Proportion the hardener and resin accurately.
2. Thoroughly mix together.
3. Use the correct product for the conditions, especially during cold weather.

6.0 PACKAGING

900g, 1.8kg, 3.6kg & 16kg packs



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.