

FAST-SETTING EPOXY GLUE EPAR GP 5 MINUTE

TECHNICAL DATA

1.0 DESCRIPTION

EPAR GP 5-MINUTE is a high strength, two-part epoxy glue. It is non-shrink and suitable for use where an adhesive with fast initial setting is required. EPAR GP 5-MINUTE has a grease-like viscosity. EPAR GP 5-MINUTE is suitable for service in either dry or wet conditions once fully cured.

2.0 PHYSICAL PROPERTIES:

2.1	Viscosity	Grease-like.
2.2	Mix Ratio	1 part resin: 1 part hardener by volume or weight.
2.3	Pot Life	5 minutes for 20 grams at 20°C.
2.4	Minimum Application Temp.	0°C.
2.5	Shelf Life	1 year.
2.6	Cured Properties	
2.6.1	Colour	Milky white
2.6.2	Specific Gravity	1.1

3.0 USES

EPAR GP 5-MINUTE is suitable for use as an adhesive or filler for wood, concrete, steel, ceramics etc.


Fields of use include:

- Manufacture of timber joinery and furniture.
- Affixing bench tops to joinery, etc.
- Boat building.
- Repair and manufacture of formwork for concrete.
- Instant repairs and quick turnover.
- Traffic stud adhesive.

4.0 APPLICATION INSTRUCTIONS

- 4.1 SURFACE PREPARATION. Thoroughly clean the surfaces of all extraneous matter, especially oil and grease. Laitance should be removed from concrete surfaces mechanically or by acid etching. For best results steel surfaces should be prepared by sand blasting or grinding.
- 4.2 MIXING. Accurately proportion required volume of resin and hardener ensuring this amount can be used within its pot life. Large volumes of mixed EPAR GP 5-MINUTE will generate considerable heat and result in reduced pot life.

Mix resin and hardener thoroughly using a spatula



Fraser Brown & Stratmore Ltd

HEAD OFFICE: 185 Rata Street, Naenae, Lower Hutt. PO Box 35 136, Naenae, Lower Hutt
Phone: (04) 567 8436 Fax: (04) 567 7232 Email: info@fbsltd.co.nz www.fbsltd.co.nz

Products for Concrete and Construction



Quality
ISO 9001

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available on request. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Fraser Brown & Stratmore Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

EPAR GP 5 MINUTE

TECHNICAL DATA Continued

- 4.3 APPLICATION. When being used as an adhesive apply an even layer of EPAR GP 5-MINUTE to jointing surfaces. The joint must be held in position until sufficient strength has been obtained. Initial set is between 5 and 10 minutes depending on temperature.
- 4.4 Important: EPAR GP 5-Minute epoxy is liable to creep and is therefore not suitable in applications where it is subject to a high constant load in one direction. In these circumstances, use a standard cure epoxy.
- 4.5 CLEAN UP. Tools and equipment may be cleaned before hardening commences by washing with EPAR Clean Up Solvent. Wash hands and skin with soap and hot water.

5.0 PACKAGING

4 litre packs.



Fraser Brown & Stratmore Ltd

HEAD OFFICE: 185 Rata Street, Naenae, Lower Hutt. PO Box 35 136, Naenae, Lower Hutt
Phone: (04) 567 8436 Fax: (04) 567 7232 Email: info@fbsltd.co.nz www.fbsltd.co.nz

Products for Concrete and Construction



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available on request. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Fraser Brown & Stratmore Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.