

Concrete Surface Retarder ETCHING FLUID

TECHNICAL DATA

1.0 DESCRIPTION

ETCHING FLUID is a water based concrete surface retarder which when applied to formwork, prevents concrete poured against it from setting to a depth of 5-10mm, for up to 48 hours. This allows the retarded concrete to be removed by hose after the forms have been stripped, resulting in an exposed aggregate finish.

2.0 PHYSICAL PROPERTIES

| | |
|--------------------------|------------------------------------------------|
| 2.1. Colour | Transparent Blue |
| 2.2. Specific Gravity | 1.1 |
| 2.3. Flash Point | ~40°C |
| 2.4. Viscosity | Low to medium |
| 2.5. Toxicity | Harmful substance. Contains Methylated Sprits. |
| 2.6. D.G. Classification | 3.1C, Flammable Liquid, N.O.S. |
| 2.7. Shelf Life | Unlimited in sealed drums as supplied |
| 2.8. Coverage | 5 - 6 m ² / litre |

3.0 USES

- 3.1. ETCHING FLUID is used to create a mechanical key on a concrete surface which is to have more concrete poured against it. An example of this is where ETCHING FLUID is painted on stop ends which confine individual pours of a floor slab. When the stop ends are removed and the retarded concrete is washed off, the resultant exposed aggregate finish makes an excellent key for the next pour.
- 3.2. ETCHING FLUID can also be used to create an architectural exposed aggregate finish on columns, beam panels, pavers and any other formed concrete surface.

4.0 APPLICATION INSTRUCTIONS

- 4.1 ETCHING FLUID may develop flammable vapours if heated above 40°C. Apply in a well-ventilated area and avoid open flames. No smoking. Keep away from ignition sources. Store in a cool location (15 – 25 degrees C). Wear protective gloves and clothing when using.
- 4.2 ETCHING FLUID is applied by brush, roller or spray and preferably allowed to dry for about 1 hour before pouring concrete.
- 4.3 ETCHING FLUID has no release value so that forms should get normal treatment with DISCRETE before application. This will prevent any build up on the stripped forms sticking after the retarded concrete has eventually set.

ETCHING FLUID

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.4 Normal concrete placed at normal temperatures should be removed within 48 hours. High strength concrete or concrete placed at high temperature will not be retarded for as long and consequently should have forms stripped and retarded concrete removed within 24 hours or sooner as determined by testing the effectiveness of ETCHING FLUID with the proposed concrete mix.
- 4.5 Treated formwork will withstand a shower, but not heavy rain, as the ETCHING FLUID is soluble in water.

5.0 PACKAGING

20 litre pails, 210 litre drums.



**Strat
more.**

Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.