

TIMBER FORMWORK SEALER FORMSEAL

TECHNICAL DATA

1.0 DESCRIPTION

FORMSEAL is a single pack coating designed to provide a flexible, abrasion resistant film on timber formwork.

FORMSEAL has excellent alkali resistance and is not affected by solvents and oils commonly used in release agents.

The use of FORMSEAL will extend the life of formwork, give improved concrete surface finish, and reduce the consumption of release agent.

2.0 PROPERTIES

2.1. Colour	Transparent Pale Yellow
2.2. Specific Gravity	0.96
2.3. Flash Point	27°C
2.4. Viscosity	Low
2.5. Toxicity	Poisonous. Contains Isocyanate & Solvent 100.
2.6. D.G. Classification	3
2.7. Shelf Life	Up to 12 months in unopened containers as supplied.
2.8. Coverage	2 coats at 6 - 8m ² /litre.

3.0 USES

FORMSEAL is suitable for use on construction ply to achieve a non-absorbent; wear resistant surface up to the specifications of melamine coated overlay ply. Up to 19 pours have been achieved off a single FORMSEAL coated construction ply form.

FORMSEAL is also ideal for use on textured timber forms such as skip-sawn ply where a uniform architectural finish is required over a number of pours.

4.0 APPLICATION INSTRUCTIONS

- 4.1. Read label in conjunction with this product data sheet.
- 4.2. SURFACE PREPARATION: Timber to be coated with FORMSEAL must be clean and dry. All traces of wax, grease and oil, must be removed. Contaminated areas should be scrubbed with a water-soluble solvent or cleaner and then thoroughly rinsed with water and allowed to completely dry. This procedure may need to be repeated to remove soaked in oil or grease. Surfaces should be thoroughly sanded to obtain a smooth finish. Use sand paper max 100 – 120 grit.

FORMSEAL

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.3. FORMSEAL is supplied ready to apply. Up to 10% FORMSEAL thinners may be added to aid application if necessary.
- 4.4. Exposure to air causes the viscosity of FORMSEAL to increase. FORMSEAL that has thickened before application should not be used. FORMSEAL to be applied should be transferred to a separate container and the storage container immediately resealed.
- 4.5. Two coats of FORMSEAL should be applied by brush, roller or spray. The first coat should be tack free before application of the second coat, minimum 6 hours drying. If more than 12 hours pass between coats the first coat should be scuffed thoroughly before application of the second coat.
- 4.6. The application rate per coat should be about 6-8m²/litre. The application of excessive film thickness *must be avoided* as this may lead to incomplete cure.
- 4.7. Allow drying time of at least 24 hours and preferably longer or until FORMSEAL has cured hard before coating forms with release agent.

5.0 PRECAUTIONS

Working areas must be adequately ventilated with free circulating air. This is necessary for both safety and to ensure complete cure of the coating.

Read and follow handling and safety information on the product label and refer to Safety Data Sheet for handling and safety precautions.

FORMSEAL is flammable. Keep containers sealed and away from heat/sparks/open flames/hot surfaces. Use explosion-proof electrical equipment. Use only non-sparking tools. Take precautionary measures against static discharge.

6.0 PACKAGING

4 & 20-litre containers.



Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.