

Polycarboxylate High Range Water Reducer/Super Plasticiser PC-707

TECHNICAL DATA

1.0 DESCRIPTION

PC-707 is a latest-generation, polycarboxylate concrete additive with high range water reducing properties to provide high workability and high early age strength.

Compared with a control sample, addition of PC-707 significantly reduces the mixing water required and therefore produces a higher-quality, reduced viscosity, more-workable concrete. PC-707 has a pronounced plasticizing effect on high-strength concrete and provides a longer working time compared to other products.

Compared with older generation low-range and mid-range water-reducing admixtures, PC-707 does not retard the mix's set time. This is important in the precast concrete industry where high early strengths are required to meet production schedules.

PC-707 may be used in a wide range of concrete applications.

2.0 PROPERTIES

2.1. Colour	Pale amber to brown, clear or slightly turbid liquid.
2.2. pH:	7
2.3. Specific Gravity	1.09
2.4. Flash Point	Non-Flammable
2.5. Viscosity	Low
2.6. Toxicity	Non-Toxic
2.7. D.G. Classification	Non-Hazardous
2.8. Shelf Life	1 year in sealed containers as supplied. Protect from frost.

3.0 USES

PC-707 can be used in:

- Site concrete to adjust slump and increase workability without adding extra water
- Fibre reinforced concrete to aid with workability without adding additional water
- Production of self-consolidating concrete mixes such as those used in the precast industry
- Concrete requiring extended workability and/or high early age compressive strength.

PC-707

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS

Usage:

PC-707 should be shaken or mixed well before using. It can be used with any cement conforming to relevant standards. PC-707 is compatible with most other admixtures. Add each admixture **separately** and check results. Adding admixtures together can produce unexpected and undesirable results. A trial batch is recommended where possible.

Batching Plant: Add PC-707 to the water prior to mixing. Allow 1 minute mixing per cubic metre of concrete. Note the effect on slump over a given time and plan deliveries accordingly.

Concrete truck: Add PC-707 directly to the mixer, then mix on maximum speed for a timed 5 minutes.

Addition:

The normal addition rate of PC-707 is 0.1 - 0.2 kg per 100 kg cement (0.1 – 0.2%).

Start at the low end of the range (0.1kg) and mix well. Increase dosage of PC-707 only if necessary.

An ideal water-to-cement ratio is 0.42 – 0.45 (depending on requirements, mix design, etc).

The exact dosage required is determined by site trials. Important considerations include accurately determining water to cement ratio, aggregate moisture correction, aggregate used, cement type, other admixtures used, etc.

DO NOT overdose with PC-707. Add a small quantity to start with and then increase only if necessary. Ensure the PC-707 is thoroughly mixed into the concrete and the change in slump checked before adding more. Excessive superplasticiser can cause the concrete to segregate. PC-707 is very efficient and less PC-707 is required compared to older generation superplasticisers.

Refer to Product Safety Data Sheet for first aid and handling information.

5.0 PACKAGING

4, 20, 200 and 1000-litre containers.



Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.