

CONCRETE SURFACE RETARDER FOR FORMWORK RETARDÉ M

TECHNICAL DATA

1.0 DESCRIPTION

RETARDÉ M is a solvent based paint-like liquid which when applied to formwork or moulds, prevents concrete poured against it from setting for up to 72 hours. This allows the retarded concrete to be removed by hose after the formwork has been stripped, resulting in an exposed aggregate finish.

2.0 PHYSICAL PROPERTIES:

2.1	Colour	Pale pink
2.2	Specific Gravity	1.1
2.3	Flashpoint	28°C Flammable
2.4	Viscosity	Liquid (Brushable)
2.5	Toxicity	Poisonous. Contains Xylene
2.6	D.G. Classification	3 (Resin Solution Flammable UN 1866)
2.7	Shelf Life	1 Year in original sealed containers as supplied
2.8	Coverage	5 – 6m ² per litre

3.0 USES

- 3.1 RETARDÉ M is used to create a mechanical key on a concrete surface which is to have more concrete poured against it. An example of this is where RETARDÉ M is painted on stop ends which confine individual pours of a floor slab. When the stop ends are removed and the retarded concrete is washed off, the resultant exposed aggregate finish makes an excellent key for the next pour.
- 3.2 RETARDÉ M can also be used to create an architectural exposed aggregate finish on columns, beams, panels, pavers and any other formed concrete surface.

4.0 APPLICATION INSTRUCTIONS

- 4.1 RETARDÉ M may settle in storage. Stir before use.
- 4.2 RETARDÉ M should be applied to formwork by brush and allowed to dry before concrete is placed against it (about 2 hours). It is recommended that forms treated with RETARDÉ M be used within 10 days of application.
- 4.3 Steel moulds or formwork sealed with FORMSEAL only require one coat but dry absorbent timber may require a second coat.
- 4.4 RETARDÉ M is resistant to light rain but should be protected from heavy rain and direct sunlight.
- 4.5 Upon removal of the formwork, preferably within 72 hours, the concrete surface must be brushed and washed immediately with low-pressure water. Much of the unset surface mortar will stick to the form during the stripping operation. This soft mortar is easily removed by water jet and a stiff broom.

RETARDÉ M

TECHNICAL DATA Continued

4.0 APPLICATION INSTRUCTIONS (continued)

- 4.6 Multiple coats of RETARDÉ M increase the dry film thickness and depth of retardation. If unusual aggregate sizes are being used it is advisable to make preliminary tests to determine the correct depth of retardation.
- 4.7 Wear protective clothing, eye protection and avoid skin contact. Avoid breathing vapours. Refer to product safety data sheet and product label for complete details.
- 4.8 Accelerating admixtures, steam curing and hot weather all reduce the effectiveness of RETARDÉ M.
- 4.9 Protect from frost.

5.0 PACKAGING

RETARDÉ M is supplied in 4 litre cans and 20 litre pails.



**Strat
more.**

Leading solutions for construction.

The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

