

# SOLVENT BASED ACRYLIC CONCRETE SEALER

## SAME DAY SEALER

### TECHNICAL DATA

#### 1.0 DESCRIPTION

SAME DAY SEALER is a single-coat solvent-based acrylic resin solution for use on concrete (normal and coloured - see precautions), to seal the surface. It is used to put a clear glaze on ground/polished concrete floors, exposed aggregate, imprinted (stamped) concrete drives, paths, etc. It helps to maintain the surface clean and prevent pigment leach-out.

SAME DAY SEALER has excellent UV and weather resistance and may be applied to green concrete surfaces. For extremely dense surfaces with little porosity, HARDCOAT is preferred.

#### 2.0 PHYSICAL PROPERTIES

2.1	Colour	Clear and colourless. Dries to a semi-gloss sheen depending on surface roughness.
2.2	Specific Gravity	0.92
2.3	Flash Point	24 °C. Flammable. Avoid all sources of ignition.
2.4	Viscosity	Low
2.5	Min. Application Temp.	5 °C substrate temperature.
2.6	Toxicity	Poisonous. Contains aromatic hydrocarbon mixture including Xylene. Non-toxic when completely dry. MSDS available on request.
2.7	D.G. Classification	Class 3 (Resin Solution Flammable, UN 1866)
2.8	Shelf Life	Over 1 yr. in original sealed container.
2.9	Coverage	Exposed Aggregate: 6 m <sup>2</sup> per litre Broomed Surface: 8 m <sup>2</sup> per litre Trowelled Surface: 12 m <sup>2</sup> per litre

Coverage is approximate depending on surface porosity.

#### 3.0 USES

SAME DAY SEALER is used to put a clear glaze on concrete and masonry surfaces such as footpaths, driveways, lock-ups, garages, industrial floors, exposed aggregate, etc where a single coat application is required.

SAME DAY SEALER provides a weatherproof (but not waterproof), stain resistant and dustproof finish. It may be used to seal dusting and porous surfaces to help against further degradation.

SAME DAY SEALER is formulated to enhance the beauty of concrete surfaces.

SAME DAY SEALER is resistant to rain, sun, water and grease offering excellent durability with good colour retention and clarity. SAME DAY SEALER is non-yellowing.

# SAME DAY SEALER

---

## TECHNICAL DATA (continued)

---

### 4.0 BENEFITS

SAME DAY SEALER offers the following benefits and advantages:

- Single coat system (an additional coat may be required depending on substrate porosity and sheen requirements).
- Can be applied to green concrete after 24 hours concrete curing. Helps concrete cure by retaining moisture.
- Touch dry in 30 minutes. Can be opened to foot traffic in one to 2 hours (exterior application with good drying conditions at 20 °C - one coat applications). Additional coats must be allowed to dry completely, approximately 12 hours under good drying conditions before being opened to traffic.
- Highly weather resistant, providing a clear, tough, easy to clean film.
- Excellent UV stability to prevent yellowing in exterior applications.
- Prevents surface dusting of concrete.
- Dries to a semi-gloss sheen depending on surface roughness. Additional coats increase gloss (up to 2 coats in total). A full gloss can be achieved if desired.
- May be used on interior concrete surfaces (good ventilation required).

### 5.0 IMPORTANT INFORMATION (read before starting application)

This data sheet provides instructions and details based on an assumption that the substrate is fit-for-purpose and free from defects and conditions that might impact the application or performance of the coating over time. For further details on this, please read the **“Stratmore Guide to Sealing Concrete”** available for download from our website.

Concrete is a porous material. Water can enter concrete by many different routes such as from rain, ground water run-off, below ground water, etc. When water enters concrete, it escapes through the pores and capillaries at different rates depending on the porosity of the concrete, the temperature, wind conditions, whether the water is transient (such as rain) or permanent (such as below ground water table), etc. Concrete that appears dry at the surface may be saturated with water further into the substrate. Applying a concrete sealer to concrete that contains excess moisture (water), depending on how thickly the sealer is applied (and the number of coats), significantly reduces or stops water vapour from being able to escape through the top (sealed) surface of the concrete. This can lead to failure of the coating, including discolouration (white/cloudy appearance or blushing), delamination (the sealer comes away from the surface), reduced service life, etc. It is therefore important to read all precautions under section 6 before starting application.



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

# SAME DAY SEALER

---

## TECHNICAL DATA (continued)

---

### 6.0 PRECAUTIONS

The following precautions are provided to guide the applicator/specifier where ideal conditions may not exist. We strongly recommend determining both the substrate moisture levels and performing a test for suitability as detailed below prior to starting the project application.

#### Determining Substrate Moisture

6.1 Before coating concrete or other suitable substrates, it is vital that you establish how much moisture it contains. The “**Stratmore Guide to Sealing Concrete**” (available for download from our website), lists methods and ways to determine how much moisture may be in the substrate. We strongly recommend that the applicator and/or specifier reads this document **before** starting application. Problems with the application of SAME DAY SEALER associated with excess moisture (as noted above and detailed in the guide) are not a product performance related issue and must be addressed by the applicator/specifier.

#### Performing a Test Application

6.2 Due to the surface variations inherent in concrete surfaces, slate and masonry products, **applicator must test SAME DAY SEALER in a small inconspicuous area before proceeding with full application** to determine if suitable for the particular application and/or our information is applicable in a particular circumstance. Where moisture may be an issue, monitor the test area for as long as practicable prior to starting the project application. Specifier and user shall determine suitability for a specific application and assume all responsibilities in connection therewith.

6.3 Determine required sheen level and sealing effectiveness by applying the required number of coats before proceeding with complete application. Substrate composition may result in random variations in porosity, thereby affecting coverage, sheen levels and sealing effectiveness. Coverage rates must be adjusted to compensate for the resulting penetration. Note that being a clear acrylic, SAME DAY SEALER will darken surfaces to which it is applied, and the effect will be greater with additional coats. Uneven substrate composition or colour will not be rectified by applying SAME DAY SEALER to the surface.

#### Application Temperature

6.4 Do not apply SAME DAY SEALER if the temperature of the substrate is below 5°C. Substrate temperature must be 3°C above the dew point. Check drying time if applied indoors and allow extra time before opening floor to traffic. Ensure good through ventilation (flame proof mechanical if required) during and after application until completely dried. Protect from rain, moisture, etc. until each coat is completely dry. For porous and/or coloured surfaces, protect from water contact until all the required coats have been applied and dried completely.



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

# SAME DAY SEALER

---

## TECHNICAL DATA (continued)

---

### 6.0 PRECAUTIONS (continued)

#### Wear & Recoating

6.5 SAME DAY SEALER will wear, but it can easily be overcoated, as it is resoluble. Wear rate will depend on the substrate and type of traffic. For vehicle traffic, SAME DAY SEALER will wear more quickly, especially in areas where wheels turn or where traffic is restricted to one location (such as a driveway) and where forklifts operate. For flooring applications, any items dragged across the SAME DAY SEALER surface will cause the surface to be scratched and wear more quickly. Before repairing damaged areas or overcoating with more SAME DAY SEALER, clean thoroughly and allow to dry. When recoating, do not exceed two coats in total (taking into account the existing coating and new coating). Also refer section 7 Application as this section also applies to recoating an existing application.

Soft rubber tyres, such as forklift tyres, may mark SAME DAY SEALER if allowed to skid on the treated surface.

#### General Precautions

- 6.6 SAME DAY SEALER is not a waterproof membrane and is not to be used as a sealer in structures containing water.
- 6.7 SAME DAY SEALER contains a mixture of aromatic hydrocarbon solvents and must be handled with care. Use in well ventilated areas. Avoid inhalation of fumes. Highly flammable - do not smoke. Keep containers sealed and away from ignition sources and heat. Wear protective clothing and avoid skin contact. If applied indoors, the area must be well ventilated and if necessary, wear self-contained breathing apparatus. If using fans for ventilation, ensure they are of a type that cannot generate sparks. Read and follow all details on the product label and safety label before use. Refer to Product Safety Data Sheet for complete handling and safety information.

### 7.0 APPLICATION INSTRUCTIONS (read in conjunction with product label)

7.1 The surface to be treated must be clean and dry prior to application (i.e. uncoated and unsoiled). Stains, oil, grease and any other surface contaminants or coatings must be removed. Old stains not removed from the surface will be visible after the film dries and difficult to remove as they will be trapped under the coating. For new concrete, do not apply over evaporation retarders or curing compounds.



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

# SAME DAY SEALER

---

## TECHNICAL DATA (continued)

---

### 7.0 APPLICATION INSTRUCTIONS (continued)

- 7.2 **New concrete:** SAME DAY SEALER is suitable for application to new concrete after 24 hours. There must be no surface water and the concrete surface must not be marred by walking workmen. **Apply only a thin coating – the product must not be over-applied.** The concrete may still appear dark due to internal water. SAME DAY SEALER helps to retain this water and assist with hydration. Over time, excess water will be lost by diffusion through the coating. The concrete will lighten in colour during this process (concrete containing calcium chloride will remain darker longer when covered with SAME DAY SEALER). Do not apply a second coat until the concrete has lost its water as evidenced by becoming lighter in colour. Do not cover the concrete during this process. See instruction 7.7.
- 7.3 **Existing concrete:** Very dense concrete surfaces should be 'deglazed' by washing with a dilute solution of Hydrochloric or MISTIC Acid, washed thoroughly to remove all acid and allowed to dry. SAME DAY SEALER is not suitable for application to non-porous surfaces, including glazed surfaces such as ceramic tiles, where it cannot penetrate the substrate. The surface must be as dry as possible to permit maximum penetration of SAME DAY SEALER. Do not apply outdoors if rain or dew is likely within 12 hours of application. Wet or damp substrates or substrates with excessive moisture content (see section 6.0) or exposure to rain or dew can cause adhesion problems or discolouration (white or cloudy appearance).
- 7.4 Read and follow the instructions under section 6.0 before proceeding with application. Apply one coat of SAME DAY SEALER as supplied at the proper coverage rate (depending upon surface absorbency). Use a solvent resistant roller (long nap for very rough surfaces such as exposed aggregate), brush or airless sprayer to apply. A single coat dries to a semi-gloss finish depending on the roughness of the surface to which it is applied. An additional coat will increase the gloss level. A full gloss can be achieved if desired. A satin finish may be achieved by applying SAME DAY SEALER SATIN as the top coat.
- 7.5 Allow to dry and assess whether the finish is as desired. If deemed necessary, apply a second coat, allow to dry and reassess. Two thin coats will give superior performance to one thick coat. **Beware of over-application as it may result in reduced ability to allow water vapour to diffuse out of the concrete and lead to blushing or blooming.** If applying by roller, use a brush to "mop up" excess material in grooves, pores and other imperfections. Do not allow excess material to pool.
- 7.6 **Application of additional coats:** When applied to green/new concrete, if a second coat is required, allow at least 14 days of good drying conditions before application of the second coat. When applied to existing concrete, the first coat must be completely dry before application of the second coat. Usually 12 hours is sufficient under good drying conditions (warm weather and air movement). **DO NOT** apply more than 2 coats in total.



The information contained in this data sheet, is to the best of our knowledge accurate and any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Users are urged to make their own assessment of our products under their own conditions and for their own requirements. Stratmore Construction Solutions Limited reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions. This data sheet may be updated without notice. Please ensure you have the latest copy. If you are a customer, then any contract with you is in accordance with our latest terms and conditions, which are available to download from our website. Where goods are acquired for business purposes, Parts 1 to 4 of the Consumers Guarantee Act 1993 will not apply. To the maximum extent permitted by law, we have no liability (whether statutory, in contract or tort, including negligence) to buyers, users or specifiers of our products for any physical, direct or indirect damage, economic loss or any other loss or costs caused or contributed by us or any of our agents or employees in respect of any goods or services supplied. Also to the maximum extent permitted by law, all conditions and warranties expressed or implied by statute or common law, equity, trade custom or usage or otherwise howsoever are excluded. If, notwithstanding the foregoing, Stratmore Construction Solutions Limited is found to have any liability, then it is agreed that the liability is nevertheless limited to the price of the relevant goods or services purchased from us.

# SAME DAY SEALER

---

## TECHNICAL DATA (continued)

---

### 7.0 APPLICATION INSTRUCTIONS (continued)

7.7 Finished application must be completely dry before opening to foot or vehicle traffic. This is a minimum of 12 hours from application of the last coat, preferably overnight. Protect application from rain, water, dew, etc. until completely dry.

Clean up with HARDCOAT Solvent or Xylene.

### 8.0 PACKAGING

4, 20 and 200 litres.

