

CEMENT MODIFIER

BOND R

TECHNICAL DATA

1.0 DESCRIPTION

Bond-R is an acrylic polymer which when added to Portland cement compositions, greatly improves their physical and chemical performance, whether used indoor or outdoor.

The improvements obtained using Bond-R are superior to those achieved using P.V.A. and styrene-butadiene emulsions. The properties improved include tensile and flexural strengths, abrasion and impact resistance, adhesion to existing concrete and resistance to oil and grease.

2.0 PROPERTIES

2.1. Colour	White.
2.2. Specific Gravity	1.07.
2.3. Flash Point	Non Flammable.
2.4. Viscosity	Low.
2.5. Toxicity	Non Toxic.
2.6. D.G. Classification	Non Hazardous.
2.7. Shelf Life	1 year in sealed containers as supplied. Protect from frost.

3.0 USES

Uses for Bond R modified concrete and plaster include;

- Heavy duty flooring.
- Topping and patching mix for existing damaged floors.
- Levelling screed or underlay for decorative flooring.
- Terrazzo.
- Precast panels.
- Patching of spalled concrete.
- Bridge deck repairs.

4.0 APPLICATION INSTRUCTIONS

- 4.1. Air and surface temperature must be 5°C or higher during and for 4 days following application. Avoid use during very hot, dry weather as this may result in fine surface cracking.
- 4.2. BOND R should not be used on floors subject to rising damp.
- 4.3. Dust, loose or weak areas must be removed. Areas badly soaked with oil or grease must be chipped out. Oil, grease or paint on the surface can be removed by scouring with a hot detergent solution. The surface must then be rinsed thoroughly with clean water and left to dry.
- 4.4. When spalled concrete is being repaired all unsound material must be removed and all rusted reinforcing exposed. Remove rust and coat exposed steel with a suitable zinc rich primer.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.



BOND R

TECHNICAL DATA Continued

4.5. PRIMING

All surfaces to be coated or patched should be primed to ensure maximum bond

4.5.1. Method A:

To a 1:1 mixture of BOND R and water add enough fresh cement to obtain a wet brushable slurry. Brush the slurry firmly into the surface to be coated and apply topping or patch material before the slurry coat has dried.

4.5.2. Method B:

Brush a mixture of 1:1 BOND R and water over the surface to be coated at approximately 6m²/litre. Allow this coat to dry for 12 hours minimum. Apply a second coat to the surface and apply topping or patch material before this coating dries.

4.6. MIXING

Dilute 1 part BOND R with between 1 and 4 parts water depending on intended use as below. Mix this liquid with the desired sand cement blend to obtain a semi-dry, plastic consistency. Mixing should not exceed one and a half minutes.

4.7. Suggested mix ratios for various applications are as follows:

4.7.1. *Heavy Duty Flooring.*

3 parts suitably graded aggregate to 1 part cement.
1 part BOND R to 1 part water as gauging liquid.

4.7.2. *Patching and Spall Repair.*

2 parts hard plastering sand to 1 part cement.
1 part BOND R to 1 part water as gauging liquid.

4.7.3. *Light Duty Levelling Screed or Underlay.*

3 parts flooring sand to 1 part cement.
1 part BOND R to 4 parts water as gauging liquid.

4.7.4. *Tile Adhesive.*

3 parts of sand to 1 part cement.
1 part BOND R to 2 parts water as gauging liquid.

4.8. LAYING

Spread the mix to the desired thickness, compact with a tamping bar and level with wooden floats. Close the surface with a metal float and do not rework after this. Do not cure with water. Avoid using during rapid drying conditions. Foot traffic may be allowed after 24 hours. Full cure is obtained after 14 days.

4.8.1. Minimum application thickness will depend on the size of aggregate in the mix and service conditions. As a guide heavy duty flooring should be a minimum of 6mm thick and light duty toppings of 1.5mm minimum.

5.0 PACKAGING

4 litre & 20 litre containers.



Fraser Brown & Stratmore Ltd

Address: 185 Rata Street, PO Box 35136 Naenae, Lower Hutt, New Zealand

Telephone: 04 567 8436 Freephone: 0800 835 699 Facsimile: 04 567 7232 Freefax: 0800 FIBRES (342 737)

Website: www.fbsltd.co.nz

Email: info@fbsltd.co.nz

The information contained in this data sheet, is to the best of our current knowledge, true and accurate, but any recommendations or suggestions which may be made are without liability on our part, since the conditions of use are beyond our control. Buyers and users are urged to make their own assessment of our products under their own conditions and for their own requirements. Fraser Brown & Stratmore Ltd reserves the right to alter formulations without notice. Properties as stated were determined under controlled laboratory conditions.

